

Listing of Claims:

1. (Original) A ceramic slurry composition comprising 20~50wt.% of a ceramic powder, 2~10wt.% of a polymer having an average molecular weight of 400,000 or more, 0.1~2wt.% of a polymer having hydrogen bond-forming functional groups, and 40~75wt.% of a solvent.
2. (Original) A ceramic slurry composition comprising 20~50wt.% of a ceramic powder, 2~10wt.% of a polymer having an average molecular weight of 400,000 or more, 0.1~2wt.% of a polymer having hydrogen bond-forming functional groups, 40~75wt.% of a solvent, and 1~5wt.% of a polymer having an average molecular weight of 400,000 or less.
3. (Currently Amended) The ceramic slurry composition according to claim 1 ~~claim 1 or 2~~, wherein the polymer is polyolefins.
4. (Currently Amended) The ceramic slurry composition according to claim 1 ~~claim 1 or 2~~, wherein the hydrogen bond-forming functional groups are selected from the group consisting of -OH, -COOH, -COOCH₃ - NH₂ and -NHCO.
5. (Original) The ceramic slurry composition according to claim 4, wherein the polymer having the hydrogen bond-forming functional groups is at least one polymer selected from the group consisting of polyvinylacetates, ethylene-acrylic acid copolymers, ethylene-ethylacryl copolymers, ethylene methylacryl copolymers, polyacrylic acids, polymethacrylic acids, polylactic acids, polyvinylbutyrals, polyvinyl alcohols, polyvinylamines, amine-derived polymers, polyurethanes, polyureas and polyamides.
6. (Original) A method for producing a thin green sheet comprising:
extruding a ceramic slurry composition to prepare an extruded sheet;
and stretching the extruded sheet,

wherein the ceramic slurry composition comprises 20~50wt.% of a ceramic powder, 2~10wt.% of a polymer having an average molecular weight of 400,000 or more, 0.1~2wt.% of a polymer having hydrogen bond-forming functional groups, and 40~75wt.% of a solvent.

7. (Original) A method for producing a thin green sheet comprising:
extruding a ceramic slurry composition to prepare an extruded sheet; and
stretching the extruded sheet,

wherein the ceramic slurry composition comprises 20~50wt.% of a ceramic powder, 2~10wt.% of a polymer having an average molecular weight of 400,000 or more, 0.1~2wt.% of a polymer having hydrogen bond-forming functional groups, 40~75wt.% of a solvent, and 1~5wt.% of a polymer having an average molecular weight of 400,000 or less.

8. (Currently Amended) An electronic device comprising:

dielectric ceramic layers;

internal electrodes interposed between the respective dielectric ceramic layers; and

external electrodes electrically connected to the 10 respective internal electrodes,

wherein the dielectric ceramic layers are 40-layer or more stacks formed by laminating green sheets, with a thickness of 10 μ m or less which are produced in accordance ~~accordance~~ with the method of claim 6 ~~claim 6 or 7~~, and the internal electrodes contain conductive components.